

Atrium Windows Doors

Series/Model	Glass Type	U-Value	SHGC	Northern	North-Central	South-Central	Southern
130 Single Hung	SS Clear Glass No Grid	0.49	0.63				
	DS Clear Glass No Grid	0.49	0.62				
	SS Low-E Glass No Grid	0.36	0.30				
	DS Low-E Glass No Grid	0.35	0.30				
	SS Low-E/Argon Glass No Grid	0.32	0.30				
	DS Low-E/Argon Glass No Grid	0.32	0.29				
	SS Ultra Low-E/Argon No Grid	0.29	0.22		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.29	0.22		MEETS	MEETS	MEETS
	SS Turtle Code Low-E No Grid	0.36	0.21				MEETS
	DS Turtle Code Low-E No Grid	0.36	0.21				MEETS
	SS Turtle Code Low-E/Argon No Grid	0.33	0.20				MEETS
	DS Turtle Code Low-E/Argon No Grid	0.33	0.20				MEETS
	SS Clear Glass with Grid	0.49	0.57				
	DS Clear Glass with Grid	0.49	0.55				
	SS Low-E Glass with Grid	0.36	0.27				
	DS Low-E Glass with Grid	0.35	0.27				
	SS Low-E/Argon Glass with Grid	0.32	0.27				
	DS Low-E/Argon Glass with Grid	0.32	0.27				
	SS Ultra Low-E/Argon with Grid	0.29	0.20		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.29	0.20		MEETS	MEETS	MEETS
	SS Turtle Code Low-E No Grid	0.36	0.19				MEETS
	DS Turtle Code Low-E No Grid	0.36	0.19				MEETS
	SS Turtle Code Low-E/Argon No Grid	0.33	0.19				MEETS
	DS Turtle Code Low-E/Argon No Grid	0.33	0.18				MEETS
	SS Clear Glass with SDL	0.49	0.50				
	DS Clear Glass with SDL	0.49	0.49				
	SS Low-E Glass with SDL	0.36	0.24				MEETS
	DS Low-E Glass with SDL	0.35	0.24				MEETS
	SS Low-E/Argon Glass with SDL	0.32	0.24				MEETS
	DS Low-E/Argon Glass with SDL	0.32	0.24				MEETS
	SS Ultra Low-E/Argon with SDL	0.29	0.18		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with SDL	0.29	0.20		MEETS	MEETS	MEETS
	SS Turtle Code Low-E with SDL	0.36	0.17				MEETS
	DS Turtle Code Low-E with SDL	0.36	0.17				MEETS
SS Turtle Code Low-E/Argon with SDL	0.33	0.17				MEETS	
DS Turtle Code Low-E/Argon with SDL	0.33	0.17				MEETS	
130 Horizontal Sliders	SS Clear Glass No Grid	0.49	0.62				
	DS Clear Glass No Grid	0.49	0.61				
	SS Low-E Glass No Grid	0.35	0.30				
	DS Low-E Glass No Grid	0.35	0.30				
	SS Low-E/Argon Glass No Grid	0.32	0.29				
	DS Low-E/Argon Glass No Grid	0.31	0.22				MEETS
	SS Ultra Low-E/Argon No Grid	0.29	0.22		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.29	0.22		MEETS	MEETS	MEETS
	SS Low-E/Argon Glass No Grid	0.31	0.22				MEETS
	DS Low-E/Argon Glass No Grid	0.31	0.22				MEETS
	SS Turtle Code Low-E No Grid	0.36	0.21				MEETS
	DS Turtle Code Low-E No Grid	0.35	0.21				MEETS
	SS Turtle Code Low-E/Argon No Grid	0.32	0.20				MEETS
	DS Turtle Code Low-E/Argon No Grid	0.32	0.20				MEETS
	SS Clear Glass with Grid	0.49	0.56				
	DS Clear Glass with Grid	0.49	0.55				
	SS Low-E Glass with Grid	0.35	0.27				
	DS Low-E Glass with Grid	0.35	0.27				
	SS Low-E/Argon Glass with Grid	0.32	0.26				
	DS Low-E/Argon Glass with Grid	0.31	0.26				
	SS Ultra Low-E/Argon with Grid	0.29	0.20		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.29	0.20		MEETS	MEETS	MEETS
	SS Turtle Code Low-E with Grid	0.36	0.19				MEETS
	DS Turtle Code Low-E with Grid	0.35	0.19				MEETS
	SS Turtle Code Low-E/Argon with Grid	0.32	0.18				MEETS
	DS Turtle Code Low-E/Argon with Grid	0.32	0.18				MEETS
	SS Clear Glass with SDL	0.49	0.50				
	DS Clear Glass with SDL	0.49	0.49				
	SS Low-E Glass with SDL	0.35	0.24				MEETS
	DS Low-E Glass with SDL	0.35	0.24				MEETS
	SS Low-E/Argon Glass with SDL	0.32	0.24				MEETS
	DS Low-E/Argon Glass with SDL	0.31	0.24				MEETS
	SS Ultra Low-E/Argon with SDL	0.29	0.20		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with SDL	0.29	0.20		MEETS	MEETS	MEETS
SS Turtle Code Low-E with SDL	0.36	0.17				MEETS	
DS Turtle Code Low-E with SDL	0.35	0.17				MEETS	
SS Turtle Code Low-E/Argon with SDL	0.32	0.17				MEETS	
DS Turtle Code Low-E/Argon with SDL	0.32	0.17				MEETS	
130 Picture WindowSpecial Shapes	DS Clear Glass No Grid	0.48	0.65				
	DS Low-E Glass No Grid	0.34	0.31				
	DS Low-E/Argon Glass No Grid	0.30	0.31		MEETS		
	DS Ultra Low-E/Argon No Grid	0.29	0.23		MEETS	MEETS	MEETS
	DS Turtle Code Low-E Glass No Grid	0.34	0.22				MEETS
	DS Turtle Code Low-E/Argon No Grid	0.30	0.21		MEETS	MEETS	MEETS
	DS Clear Glass with Grid	0.48	0.58				
	DS Low-E Glass with Grid	0.34	0.28				
	DS Low-E/Argon Glass with Grid	0.30	0.28		MEETS		
	DS Ultra Low-E/Argon with Grid	0.29	0.21		MEETS	MEETS	MEETS
DS Turtle Code Low-E Glass with Grid	0.34	0.20				MEETS	

Atrium Windows Doors

	DS Turtle Code Low-E/Argon with Grid	0.30	0.19		MEETS	MEETS	MEETS
	DS Clear Glass with SDL	0.48	0.52				
	DS Low-E Glass with SDL	0.34	0.25				MEETS
	DS Low-E/Argon Glass with SDL	0.30	0.25		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with SDL	0.29	0.19		MEETS	MEETS	MEETS
	DS Turtle Code Low-E Glass with SDL	0.34	0.18				MEETS
	DS Turtle Code Low-E/Argon with SDL	0.30	0.18		MEETS	MEETS	MEETS
5700 Single Hung	SS Clear Glass No Grid	0.49	0.66				
	DS Clear Glass No Grid	0.49	0.64				
	SS Low-E Glass No Grid	0.34	0.31				
	DS Low-E Glass No Grid	0.34	0.31				
	SS Low-E/Argon Glass No Grid	0.31	0.31				
5700 Single Hung	DS Low-E/Argon Glass No Grid	0.30	0.31		MEETS		
	SS Ultra Low-E No Grid	0.34	0.23				MEETS
	DS Ultra Low-E No Grid	0.34	0.23				MEETS
	SS Ultra Low-E/Argon No Grid	0.30	0.23		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.30	0.23		MEETS	MEETS	MEETS
	SS Clear Glass with Grid	0.49	0.59				
	DS Clear Glass with with Grid	0.49	0.58				
	SS Low-E Glass with with Grid	0.34	0.28				
	DS Low-E Glass with with Grid	0.34	0.28				
	SS Low-E/Argon Glass with with Grid	0.31	0.28				
	DS Low-E/Argon Glass with with Grid	0.30	0.28		MEETS		
	SS Ultra Low-E with with Grid	0.34	0.21				MEETS
	DS Ultra Low-E with with Grid	0.34	0.21				MEETS
	SS Ultra Low-E/Argon with with Grid	0.30	0.21		MEETS	MEETS	MEETS
DS Ultra Low-E/Argon with with Grid	0.30	0.21		MEETS	MEETS	MEETS	
5700 Horizontal Slider	SS Clear Glass No Grid	0.49	0.66				
	DS Clear Glass No Grid	0.49	0.64				
	SS Low-E Glass No Grid	0.34	0.31				
	DS Low-E Glass No Grid	0.34	0.31				
	SS Low-E/Argon Glass No Grid	0.31	0.31				
	DS Low-E/Argon Glass No Grid	0.30	0.31		MEETS		
	SS Ultra Low-E/Argon No Grid	0.30	0.23		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.30	0.23		MEETS	MEETS	MEETS
	SS Clear Glass with Grid	0.49	0.59				
	DS Clear Glass with with Grid	0.49	0.58				
	SS Low-E Glass with with Grid	0.34	0.28				
	DS Low-E Glass with with Grid	0.34	0.28				
	SS Low-E/Argon Glass with with Grid	0.31	0.28				
	DS Low-E/Argon Glass with with Grid	0.30	0.28		MEETS		
SS Ultra Low-E/Argon with with Grid	0.30	0.21		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon with with Grid	0.30	0.21		MEETS	MEETS	MEETS	
150/160 Single Hung	SS Clear Glass No Grid	0.49	0.62				
	DS Clear Glass No Grid	0.49	0.61				
	SS Low-E Glass No Grid	0.35	0.29				
	DS Low-E Glass No Grid	0.35	0.29				
	SS Low-E/Argon Glass No Grid	0.32	0.29				
	DS Low-E/Argon Glass No Grid	0.32	0.29				
	SS Ultra Low-E/Argon No Grid	0.30	0.22		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.30	0.22		MEETS	MEETS	MEETS
	DS Northern Energy Star No Grid	0.27	0.22		MEETS	MEETS	MEETS
	SS Clear Glass with Grid	0.49	0.56				
	DS Clear Glass with Grid	0.49	0.55				
	SS Low-E Glass with Grid	0.35	0.27				
	DS Low-E Glass with Grid	0.35	0.26				
	SS Low-E/Argon Glass with Grid	0.32	0.26				
	DS Low-E/Argon Glass with Grid	0.32	0.26				
	SS Ultra Low-E/Argon with Grid	0.30	0.20		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.30	0.20		MEETS	MEETS	MEETS
	DS Northern Energy Star with Grid	0.27	0.20		MEETS	MEETS	MEETS
	SS Clear Glass with SDL	0.49	0.50				
	DS Clear Glass with SDL	0.51	0.49				
	SS Low-E Glass with SDL	0.36	0.27				
	DS Low-E Glass with SDL	0.39	0.27				
	SS Low-E/Argon Glass with SDL	0.32	0.26				
	DS Low-E/Argon Glass with SDL	0.34	0.24				MEETS
SS Ultra Low-E/Argon Glass with SDL	0.30	0.20		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon Glass with SDL	0.32	0.20				MEETS	
151/161 Horizontal Sliders	SS Clear Glass No Grid	0.48	0.62				
	DS Clear Glass No Grid	0.48	0.61				
	SS Low-E Glass No Grid	0.35	0.29				
	DS Low-E Glass No Grid	0.35	0.29				
	SS Low-E/Argon Glass No Grid	0.31	0.29				
	DS Low-E/Argon Glass No Grid	0.31	0.29				
	SS Ultra Low-E/Argon No Grid	0.29	0.22		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.29	0.22		MEETS	MEETS	MEETS
	DS Northern Energy Star No Grid	0.27	0.21		MEETS	MEETS	MEETS
	SS Clear Glass with Grid	0.48	0.56				
	DS Clear Glass with Grid	0.48	0.55				
	SS Low-E Glass with Grid	0.35	0.26				
	DS Low-E Glass with Grid	0.35	0.26				
	SS Low-E/Argon Glass with Grid	0.31	0.26				
DS Low-E/Argon Glass with Grid	0.31	0.26					

Atrium Windows Doors

	SS Ultra Low-E/Argon with Grid	0.29	0.20		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.29	0.20		MEETS	MEETS	MEETS
	DS Northern Energy Star with Grid	0.27	0.19	MEETS	MEETS	MEETS	MEETS
	SS Clear Glass with SDL	0.49	0.50				
	DS Clear Glass with SDL	0.50	0.49				
	SS Low-E Glass with SDL	0.35	0.27				
	DS Low-E Glass with SDL	0.38	0.27				
	SS Low-E/Argon Glass with SDL	0.31	0.26				
	DS Low-E/Argon Glass with SDL	0.33	0.26				
	SS Ultra Low-E/Argon Glass with SDL	0.29	0.20	MEETS	MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon Glass with SDL	0.32	0.20				MEETS
150 Picture WindowSpecial Shapes	DS Clear Glass No Grid	0.47	0.63				
	DS Low-E Glass No Grid	0.33	0.31				
	DS Low-E/Argon Glass No Grid	0.29	0.30		MEETS		
	DS Ultra Low-E/Argon No Grid	0.27	0.23	MEETS	MEETS	MEETS	MEETS
	DS Northern Energy Star No Grid	0.27	0.23	MEETS	MEETS	MEETS	MEETS
	DS Clear Glass with Grid	0.47	0.57				
	DS Low-E Glass with Grid	0.33	0.28				
	DS Low-E/Argon Glass with Grid	0.29	0.27		MEETS		
	DS Ultra Low-E/Argon with Grid	0.27	0.21	MEETS	MEETS	MEETS	MEETS
	DS Northern Energy Star with Grid	0.27	0.21	MEETS	MEETS	MEETS	MEETS
150 Picture WindowSpecial Shapes	DS Clear Glass with SDL	0.47	0.51				
	DS Low-E Glass with SDL	0.33	0.28				
	DS Low-E/Argon Glass with SDL	0.29	0.27		MEETS		
	DS Ultra Low-E/Argon Glass with SDL	0.27	0.19	MEETS	MEETS	MEETS	MEETS
	SS Clear Glass No Grid	0.47	0.58				
	DS Clear Glass No Grid	0.47	0.57				
	SS Low-E Glass No Grid	0.35	0.28				
	DS Low-E Glass No Grid	0.35	0.28				
	SS Low-E/Argon Glass No Grid	0.32	0.27				
	DS Low-E/Argon Glass No Grid	0.32	0.27				
450/455/460/465 Double Hung	SS Ultra Low-E/Argon No Grid	0.30	0.20		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.30	0.20		MEETS	MEETS	MEETS
	SS Northern Energy Star No Grid	0.28	0.38	MEETS	MEETS		
	DS Northern Energy Star No Grid	0.28	0.37	MEETS	MEETS		
	SS Clear Glass with Grid	0.47	0.52				
	DS Clear Glass with Grid	0.47	0.51				
	SS Low-E Glass with Grid	0.35	0.25				MEETS
	DS Low-E Glass with Grid	0.35	0.25				MEETS
	SS Low-E/Argon Glass with Grid	0.32	0.25				MEETS
	DS Low-E/Argon Glass with Grid	0.32	0.25				MEETS
	SS Ultra Low-E/Argon with Grid	0.30	0.18		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.30	0.18		MEETS	MEETS	MEETS
	SS Northern Energy Star with Grid	0.28	0.34	MEETS	MEETS		
	DS Northern Energy Star with Grid	0.28	0.33	MEETS	MEETS		
	SS Clear Glass with SDL	0.48	0.46				
	DS Clear Glass with SDL	0.49	0.45				
	SS Low-E Glass with SDL	0.35	0.25				MEETS
	DS Low-E Glass with SDL	0.36	0.25				MEETS
	SS Low-E/Argon Glass with SDL	0.31	0.25				MEETS
	DS Low-E/Argon Glass with SDL	0.32	0.25				MEETS
SS Ultra Low-E/Argon Glass with SDL	0.30	0.17		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon Glass with SDL	0.30	0.17		MEETS	MEETS	MEETS	
451/461 Horizontal Sliders	SS Clear Glass No Grid	0.47	0.59				
	DS Clear Glass No Grid	0.47	0.58				
	SS Low-E Glass No Grid	0.34	0.28				
	DS Low-E Glass No Grid	0.34	0.28				
	SS Low-E/Argon Glass No Grid	0.30	0.28		MEETS		
	DS Low-E/Argon Glass No Grid	0.30	0.28		MEETS		
	SS Ultra Low-E/Argon No Grid	0.30	0.21		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.29	0.21		MEETS	MEETS	MEETS
	SS Northern Energy Star No Grid	0.28	0.38	MEETS	MEETS		
	DS Northern Energy Star No Grid	0.28	0.38	MEETS	MEETS		
	SS Clear Glass with Grid	0.47	0.53				
	DS Clear Glass with Grid	0.47	0.52				
	SS Low-E Glass with Grid	0.34	0.25				MEETS
	DS Low-E Glass with Grid	0.34	0.25				MEETS
	SS Low-E/Argon Glass with Grid	0.30	0.25		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with Grid	0.30	0.25		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon with Grid	0.29	0.19		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.29	0.19		MEETS	MEETS	MEETS
	SS Northern Energy Star with Grid	0.28	0.34	MEETS	MEETS		
	DS Northern Energy Star with Grid	0.28	0.34	MEETS	MEETS		
SS Clear Glass with SDL	0.48	0.49					
DS Clear Glass with SDL	0.48	0.48					
SS Low-E Glass with SDL	0.34	0.25				MEETS	
DS Low-E Glass with SDL	0.35	0.25				MEETS	
SS Low-E/Argon Glass with SDL	0.30	0.25		MEETS	MEETS	MEETS	
DS Low-E/Argon Glass with SDL	0.31	0.25				MEETS	
SS Ultra Low-E/Argon Glass with SDL	0.32	0.17				MEETS	
DS Ultra Low-E/Argon Glass with SDL	0.32	0.17				MEETS	
	DS Clear Glass No Grid	0.44	0.62				
	DS Low-E Glass No Grid	0.30	0.30		MEETS		
	DS Low-E/Argon Glass No Grid	0.26	0.30	MEETS	MEETS		
	DS Ultra Low-E/Argon No Grid	0.26	0.22	MEETS	MEETS	MEETS	MEETS

Atrium Windows Doors

450/460 Picture WindowSpecial Shapes	DS Northern Energy Star No Grid	0.26	0.40	MEETS	MEETS		
	DS Clear Glass with Grid	0.44	0.56				
	DS Low-E Glass with Grid	0.30	0.27		MEETS		
	DS Low-E/Argon Glass with Grid	0.26	0.27	MEETS	MEETS		
	DS Ultra Low-E/Argon with Grid	0.26	0.20	MEETS	MEETS	MEETS	MEETS
	DS Northern Energy Star with Grid	0.26	0.36	MEETS	MEETS		
	DS Clear Glass with SDL	0.44	0.50				
	DS Low-E Glass with SDL	0.30	0.27		MEETS		
	DS Low-E/Argon Glass with SDL	0.26	0.27	MEETS	MEETS		
	DS Ultra Low-E/Argon Glass with SDL	0.30	0.18	MEETS	MEETS	MEETS	MEETS
315 Transom	DS Clear Glass No Grid	0.47	0.68				
	DS Low-E Glass No Grid	0.32	0.32				
	DS Low-E/Argon Glass No Grid	0.28	0.32		MEETS		
	DS Ultra Low-E/Argon No Grid	0.28	0.24		MEETS	MEETS	MEETS
	DS Clear Glass with Grid	0.47	0.61				
	DS Low-E Glass with Grid	0.32	0.29				
	DS Low-E/Argon Glass with Grid	0.28	0.29		MEETS		
	DS Ultra Low-E/Argon with Grid	0.28	0.22		MEETS	MEETS	MEETS
	DS Clear Glass with SDL	0.47	0.61				
	DS Low-E Glass with SDL	0.32	0.29				
DS Ultra Low-E/Argon Glass with SDL	0.28	0.29		MEETS			
DS Low-E/Argon Glass with SDL	0.28	0.22		MEETS	MEETS	MEETS	
316 Side Lite	DS Clear Glass No Grid	0.46	0.63				
	DS Low-E Glass No Grid	0.33	0.30				
	DS Low-E/Argon Glass No Grid	0.29	0.30		MEETS		
	DS Ultra Low-E/Argon No Grid	0.28	0.22		MEETS	MEETS	MEETS
	DS Clear Glass with Grid	0.46	0.57				
	DS Low-E Glass with Grid	0.33	0.27				
	DS Low-E/Argon Glass with Grid	0.29	0.27		MEETS		
	DS Ultra Low-E/Argon with Grid	0.28	0.20		MEETS	MEETS	MEETS
	DS Clear Glass with SDL	0.46	0.57				
	DS Low-E Glass with SDL	0.33	0.27				
DS Low-E/Argon Glass with SDL	0.29	0.27		MEETS			
DS Ultra Low-E/Argon Glass with SDL	0.28	0.20		MEETS	MEETS	MEETS	
335 Transom	DS Clear Glass No Grid	0.48	0.63				
	DS Low-E Glass No Grid	0.33	0.32				
	DS Low-E/Argon Glass No Grid	0.29	0.32		MEETS		
	DS Ultra Low-E/Argon No Grid	0.30	0.22		MEETS	MEETS	MEETS
	DS Clear Glass with Grid	0.48	0.56				
	DS Low-E Glass with Grid	0.33	0.29				
	DS Low-E/Argon Glass with Grid	0.29	0.29		MEETS		
	DS Ultra Low-E/Argon with Grid	0.30	0.20		MEETS	MEETS	MEETS
	DS Clear Glass with SDL	0.48	0.51				
	DS Low-E Glass with SDL	0.33	0.29				
DS Low-E/Argon Glass with SDL	0.29	0.29		MEETS			
DS Ultra Low-E/Argon Glass with SDL	0.28	0.21		MEETS	MEETS	MEETS	
336 Side Lite	DS Clear Glass No Grid	0.47	0.65				
	DS Low-E Glass No Grid	0.33	0.30				
	DS Low-E/Argon Glass No Grid	0.30	0.30		MEETS		
	DS Ultra Low-E/Argon No Grid	0.29	0.22		MEETS	MEETS	MEETS
	DS Clear Glass with Grid	0.47	0.56				
	DS Low-E Glass with Grid	0.33	0.27				
	DS Low-E/Argon Glass with Grid	0.30	0.27		MEETS		
	DS Ultra Low-E/Argon with Grid	0.29	0.20		MEETS	MEETS	MEETS
	DS Clear Glass with SDL	0.47	0.50				
	DS Low-E Glass with SDL	0.33	0.27				
DS Low-E/Argon Glass with SDL	0.30	0.27		MEETS			
DS Ultra Low-E/Argon Glass with SDL	0.29	0.20		MEETS	MEETS	MEETS	
8100 Single-Hung	SS Clear Glass No Grid	0.49	0.62				
	DS Clear Glass No Grid	0.49	0.61				
	SS Low-E Glass No Grid	0.36	0.29				
	DS Low-E Glass No Grid	0.36	0.29				
	SS Low-E/Argon Glass No Grid	0.33	0.29				
	DS Low-E/Argon Glass No Grid	0.32	0.29				
	SS Ultra Low-E/Argon No Grid	0.30	0.22		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.30	0.22		MEETS	MEETS	MEETS
	SS Clear Glass with Grid	0.49	0.55				
	DS Clear Glass with Grid	0.49	0.54				
	SS Low-E Glass with Grid	0.36	0.26				
	DS Low-E Glass with Grid	0.36	0.26				
	SS Low-E/Argon Glass with Grid	0.33	0.26				
	DS Low-E/Argon Glass with Grid	0.32	0.26				
SS Ultra Low-E/Argon with Grid	0.30	0.20		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon with Grid	0.30	0.20		MEETS	MEETS	MEETS	
8100 Horizontal Sliders	SS Clear Glass No Grid	0.48	0.62				
	DS Clear Glass No Grid	0.48	0.61				
	SS Low-E Glass No Grid	0.34	0.29				
	DS Low-E Glass No Grid	0.34	0.29				
	SS Low-E/Argon Glass No Grid	0.31	0.29				
	DS Low-E/Argon Glass No Grid	0.31	0.29				
	SS Ultra Low-E/Argon No Grid	0.30	0.22		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.30	0.22		MEETS	MEETS	MEETS
	SS Clear Glass with Grid	0.48	0.55				
	DS Clear Glass with Grid	0.48	0.54				
SS Low-E Glass with Grid	0.34	0.26					

Atrium Windows Doors

	DS Low-E Glass with Grid	0.34	0.26				
	SS Low-E/Argon Glass with Grid	0.31	0.26				
	DS Low-E/Argon Glass with Grid	0.31	0.26				
	SS Ultra Low-E/Argon with Grid	0.30	0.20	MEETS	MEETS	MEETS	
	DS Ultra Low-E/Argon with Grid	0.30	0.20	MEETS	MEETS	MEETS	
8100 Picture Window Special Shapes	DS Clear Glass No Grid	0.45	0.63				
	DS Low-E Glass No Grid	0.30	0.30	MEETS			
	DS Low-E/Argon Glass No Grid	0.26	0.30	MEETS	MEETS		
	DS Ultra Low-E/Argon No Grid	0.26	0.22	MEETS	MEETS	MEETS	MEETS
	DS Clear Glass with Grid	0.45	0.57				
	DS Low-E Glass with Grid	0.30	0.28		MEETS		
	DS Low-E/Argon Glass with Grid	0.26	0.27	MEETS	MEETS		
	DS Ultra Low-E/Argon with Grid	0.26	0.20	MEETS	MEETS	MEETS	MEETS
8300 Double Hung	SS Clear Glass No Grid	0.47	0.61				
	DS Clear Glass No Grid	0.47	0.60				
	SS Low-E Glass No Grid	0.34	0.29				
	DS Low-E Glass No Grid	0.34	0.29				
	SS Low-E/Argon Glass No Grid	0.31	0.29				
	DS Low-E/Argon Glass No Grid	0.31	0.28				
	SS Ultra Low-E/Argon No Grid	0.30	0.21		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.30	0.21		MEETS	MEETS	MEETS
	SS Northern Energy Star No Grid	0.29	0.39	MEETS	MEETS		
	DS Northern Energy Star No Grid	0.29	0.38	MEETS	MEETS		
	SS Clear Glass with Grid	0.47	0.54				
	DS Clear Glass with Grid	0.47	0.53				
	SS Low-E Glass with Grid	0.34	0.26				
	DS Low-E Glass with Grid	0.34	0.26				
	SS Low-E/Argon Glass with Grid	0.31	0.26				
	DS Low-E/Argon Glass with Grid	0.31	0.26				
	SS Ultra Low-E/Argon with Grid	0.30	0.19		MEETS	MEETS	MEETS
DS Ultra Low-E/Argon with Grid	0.30	0.19		MEETS	MEETS	MEETS	
SS Northern Energy Star with Grid	0.28	0.35	MEETS	MEETS			
DS Northern Energy Star with Grid	0.28	0.34	MEETS	MEETS			
8300 Picture Window	DS Clear Glass No Grid	0.45	0.65				
	DS Low-E Glass No Grid	0.30	0.31		MEETS		
	DS Low-E/Argon Glass No Grid	0.26	0.31	MEETS	MEETS		
	DS Ultra Low-E/Argon No Grid	0.25	0.23	MEETS	MEETS	MEETS	MEETS
	DS Northern Energy Star No Grid	0.26	0.42	MEETS			
	DS Clear Glass with Grid	0.45	0.58				
	DS Low-E Glass with Grid	0.30	0.28		MEETS		
	DS Low-E/Argon Glass with Grid	0.26	0.28	MEETS	MEETS		
	DS Ultra Low-E/Argon with Grid	0.25	0.21	MEETS	MEETS	MEETS	MEETS
DS Northern Energy Star with Grid	0.26	0.38	MEETS	MEETS			
8300 Horizontal Sliders	SS Clear Glass No Grid	0.48	0.63				
	DS Clear Glass No Grid	0.48	0.61				
8300 Horizontal Sliders	SS Low-E Glass No Grid	0.34	0.30				
	DS Low-E Glass No Grid	0.34	0.30				
	SS Low-E/Argon Glass No Grid	0.31	0.29				
	DS Low-E/Argon Glass No Grid	0.31	0.29				
	SS Ultra Low-E/Argon No Grid	0.30	0.22		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.30	0.22		MEETS	MEETS	MEETS
	SS Northern Energy Star No Grid	0.28	0.40	MEETS	MEETS		
	DS Northern Energy Star No Grid	0.28	0.36	MEETS	MEETS		
	SS Clear Glass with Grid	0.48	0.56				
	DS Clear Glass with Grid	0.48	0.55				
	SS Low-E Glass with Grid	0.34	0.27				
	DS Low-E Glass with Grid	0.34	0.27				
	SS Low-E/Argon Glass with Grid	0.31	0.27				
	DS Low-E/Argon Glass with Grid	0.31	0.26				
	SS Ultra Low-E/Argon with Grid	0.30	0.20		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.30	0.20		MEETS	MEETS	MEETS
	SS Northern Energy Star with Grid	0.28	0.36	MEETS	MEETS		
DS Northern Energy Star with Grid	0.28	0.36	MEETS	MEETS			
8700 Double Hung	SS Clear Glass No Grid	0.47	0.60				
	DS Clear Glass No Grid	0.47	0.59				
	SS Low-E Glass No Grid	0.34	0.28				
	DS Low-E Glass No Grid	0.34	0.28				
	SS Low-E/Argon Glass No Grid	0.31	0.28				
	DS Low-E/Argon Glass No Grid	0.31	0.28				
	SS Ultra Low-E/Argon No Grid	0.29	0.21		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.29	0.21		MEETS	MEETS	MEETS
	SS Northern Energy Star No Grid	0.28	0.38	MEETS	MEETS		
	DS Northern Energy Star No Grid	0.28	0.38	MEETS	MEETS		
	SS Clear Glass with Grid	0.47	0.54				
	DS Clear Glass with Grid	0.47	0.52				
	SS Low-E Glass with Grid	0.34	0.25				MEETS
	DS Low-E Glass with Grid	0.34	0.25				MEETS
	SS Low-E/Argon Glass with Grid	0.31	0.25				MEETS
	DS Low-E/Argon Glass with Grid	0.31	0.25				MEETS
	SS Ultra Low-E/Argon with Grid	0.29	0.19		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.29	0.19		MEETS	MEETS	MEETS
	SS Northern Energy Star with Grid	0.28	0.34	MEETS	MEETS		
	DS Northern Energy Star with Grid	0.28	0.34	MEETS	MEETS		
SS Clear Glass with SDL	0.48	0.48					
DS Clear Glass with SDL	0.49	0.47					

Atrium Windows Doors

	SS Low-E Glass with SDL	0.35	0.23				MEETS
	DS Low-E Glass with SDL	0.38	0.23				MEETS
	SS Low-E/Argon Glass with SDL	0.31	0.23				MEETS
	DS Low-E/Argon Glass with SDL	0.33	0.23				MEETS
	SS Ultra Low-E/Argon Glass with SDL	0.32	0.17				MEETS
	DS Ultra Low-E/Argon Glass with SDL	0.32	0.17				MEETS
8700 Picture Window	DS Clear Glass No Grid	0.45	0.65				
	DS Low-E Glass No Grid	0.30	0.31		MEETS		
	DS Low-E/Argon Glass No Grid	0.26	0.31	MEETS	MEETS		
	DS Ultra Low-E/Argon No Grid	0.25	0.23	MEETS	MEETS	MEETS	MEETS
	DS Northern Energy Star No Grid	0.26	0.42	MEETS			
	DS Clear Glass with Grid	0.45	0.58				
	DS Low-E Glass with Grid	0.30	0.28		MEETS		
	DS Low-E/Argon Glass with Grid	0.26	0.28	MEETS	MEETS		
	DS Ultra Low-E/Argon with Grid	0.25	0.21	MEETS	MEETS	MEETS	MEETS
	DS Northern Energy Star with Grid	0.26	0.38	MEETS	MEETS		
	DS Clear Glass with SDL	0.45	0.52				
	DS Low-E Glass with SDL	0.30	0.25		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with SDL	0.26	0.25	MEETS	MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon Glass with SDL	0.25	0.19	MEETS	MEETS	MEETS	MEETS
	8700 Horizontal Sliders	SS Clear Glass No Grid	0.46	0.62			
DS Clear Glass No Grid		0.46	0.60				
SS Low-E Glass No Grid		0.33	0.29				
DS Low-E Glass No Grid		0.33	0.29				
SS Low-E/Argon Glass No Grid		0.30	0.29		MEETS		
DS Low-E/Argon Glass No Grid		0.29	0.29		MEETS		
SS Ultra Low-E/Argon No Grid		0.29	0.21		MEETS	MEETS	MEETS
DS Ultra Low-E/Argon No Grid		0.29	0.21		MEETS	MEETS	MEETS
SS Northern Energy Star No Grid		0.28	0.39	MEETS	MEETS		
DS Northern Energy Star No Grid		0.28	0.39	MEETS	MEETS		
SS Clear Glass with Grid		0.47	0.55				
DS Clear Glass with Grid		0.47	0.54				
SS Low-E Glass with Grid		0.33	0.26				
DS Low-E Glass with Grid		0.33	0.26				
SS Low-E/Argon Glass with Grid		0.30	0.26		MEETS		
DS Low-E/Argon Glass with Grid		0.29	0.26		MEETS		
SS Ultra Low-E/Argon with Grid		0.29	0.19		MEETS	MEETS	MEETS
DS Ultra Low-E/Argon with Grid		0.29	0.19		MEETS	MEETS	MEETS
SS Northern Energy Star with Grid		0.28	0.35	MEETS	MEETS		
DS Northern Energy Star with Grid		0.28	0.35	MEETS	MEETS		
SS Clear Glass with SDL		0.47	0.49				
DS Clear Glass with SDL		0.48	0.48				
SS Low-E Glass with SDL		0.33	0.24				MEETS
DS Low-E Glass with SDL		0.37	0.24				MEETS
SS Low-E/Argon Glass with SDL		0.29	0.23		MEETS	MEETS	MEETS
DS Low-E/Argon Glass with SDL	0.32	0.23				MEETS	
SS Ultra Low-E/Argon Glass with SDL	0.29	0.18		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon Glass with SDL	0.31	0.18		MEETS	MEETS	MEETS	
600 Hopper	DS Clear Glass No Grid	0.44	0.57				
700/750 Picture Window Special Shapes	DS Clear Glass No Grid	0.47	0.67				
	DS Low-E Glass No Grid	0.31	0.32				
	DS Low-E/Argon Glass No Grid	0.28	0.32		MEETS		
	DS Ultra Low-E/Argon No Grid	0.27	0.24	MEETS	MEETS	MEETS	MEETS
	DS Clear Glass with Grid	0.47	0.60				
	DS Low-E Glass with Grid	0.31	0.29				
	DS Low-E/Argon Glass with Grid	0.28	0.29		MEETS		
700/750 Picture Window Special Shapes	DS Ultra Low-E/Argon with Grid	0.27	0.21	MEETS	MEETS	MEETS	MEETS
	DS Clear Glass with SDL	0.47	0.54				
	DS Low-E Glass with SDL	0.31	0.29				
	DS Low-E/Argon Glass with SDL	0.28	0.29		MEETS		
	DS Ultra Low-E/Argon Glass with SDL	0.27	0.21	MEETS	MEETS	MEETS	MEETS
700/750 Casement	SS Clear Glass No Grid	0.42	0.53				
	DS Clear Glass No Grid	0.42	0.52				
	SS Low-E Glass No Grid	0.31	0.25				MEETS
	DS Low-E Glass No Grid	0.31	0.25				MEETS
	SS Low-E/Argon Glass No Grid	0.28	0.25		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass No Grid	0.28	0.25		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon No Grid	0.27	0.19	MEETS	MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.27	0.19	MEETS	MEETS	MEETS	MEETS
	SS Clear Glass with Grid	0.42	0.48				
	DS Clear Glass with Grid	0.42	0.47				
	SS Low-E Glass with Grid	0.31	0.23				MEETS
	DS Low-E Glass with Grid	0.31	0.23				MEETS
	SS Low-E/Argon Glass with Grid	0.28	0.23		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with Grid	0.28	0.23		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon with Grid	0.27	0.17	MEETS	MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.27	0.17	MEETS	MEETS	MEETS	MEETS
	SS Clear Glass with SDL	0.42	0.44				
	DS Clear Glass with SDL	0.42	0.43				
	SS Low-E Glass with SDL	0.31	0.23				MEETS
	DS Low-E Glass with SDL	0.31	0.23				MEETS
	SS Low-E/Argon Glass with SDL	0.28	0.23		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with SDL	0.28	0.23		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon Glass with SDL	0.28	0.17		MEETS	MEETS	MEETS
DS Ultra Low-E/Argon Glass with SDL	0.28	0.17		MEETS	MEETS	MEETS	

Atrium Windows Doors

705/755 Awning	SS Clear Glass No Grid	0.43	0.53				
	DS Clear Glass No Grid	0.43	0.52				
	SS Low-E Glass No Grid	0.31	0.25				MEETS
	DS Low-E Glass No Grid	0.31	0.25				MEETS
	SS Low-E/Argon Glass No Grid	0.28	0.25		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass No Grid	0.28	0.25		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon No Grid	0.28	0.19		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.28	0.18		MEETS	MEETS	MEETS
	SS Clear Glass with Grid	0.43	0.48				
	DS Clear Glass with Grid	0.43	0.52				
	SS Low-E Glass with Grid	0.31	0.23				MEETS
	DS Low-E Glass with Grid	0.31	0.23				MEETS
	SS Low-E/Argon Glass with Grid	0.28	0.23		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with Grid	0.28	0.23		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon with Grid	0.28	0.17		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.28	0.17		MEETS	MEETS	MEETS
	SS Clear Glass with SDL	0.43	0.44				
	DS Clear Glass with SDL	0.43	0.43				
	SS Low-E Glass with SDL	0.31	0.23				MEETS
	DS Low-E Glass with SDL	0.31	0.23				MEETS
SS Low-E/Argon Glass with SDL	0.28	0.23		MEETS	MEETS	MEETS	
DS Low-E/Argon Glass with SDL	0.28	0.23		MEETS	MEETS	MEETS	
SS Ultra Low-E/Argon Glass with SDL	0.28	0.17		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon Glass with SDL	0.28	0.17		MEETS	MEETS	MEETS	
8900 Double Hung Dual Pane IG	SS Clear Glass No Grid	0.45	0.57				
	DS Clear Glass No Grid	0.45	0.56				
	SS Low-E Glass No Grid	0.32	0.27				
	DS Low-E Glass No Grid	0.32	0.27				
	SS Low-E/Argon Glass No Grid	0.29	0.27		MEETS		
	DS Low-E/Argon Glass No Grid	0.29	0.27		MEETS		
	SS Ultra Low-E/Argon No Grid	0.29	0.20		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.29	0.20		MEETS	MEETS	MEETS
	SS Northern Energy Star No Grid	0.28	0.37		MEETS	MEETS	
	DS Northern Energy Star No Grid	0.28	0.36		MEETS	MEETS	
	SS Clear Glass with Grid	0.45	0.51				
	DS Clear Glass with Grid	0.45	0.50				
	SS Low-E Glass with Grid	0.32	0.24				MEETS
	DS Low-E Glass with Grid	0.32	0.24				MEETS
	SS Low-E/Argon Glass with Grid	0.29	0.24		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with Grid	0.29	0.24		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon with Grid	0.29	0.18		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.29	0.18		MEETS	MEETS	MEETS
	SS Northern Energy Star with Grid	0.28	0.33		MEETS	MEETS	
	DS Northern Energy Star with Grid	0.28	0.32		MEETS	MEETS	
SS Clear Glass with SDL	0.45	0.45					
DS Clear Glass with SDL	0.45	0.44					
SS Low-E Glass with SDL	0.32	0.24				MEETS	
DS Low-E Glass with SDL	0.32	0.24				MEETS	
SS Low-E/Argon Glass with SDL	0.29	0.24		MEETS	MEETS	MEETS	
DS Low-E/Argon Glass with SDL	0.29	0.24		MEETS	MEETS	MEETS	
SS Ultra Low-E/Argon with SDL	0.29	0.16		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon with SDL	0.29	0.16		MEETS	MEETS	MEETS	
8900 Double Hung	SS Clear Glass No Grid	0.45	0.57				
	DS Clear Glass No Grid	0.45	0.56				
	SS Low-E Glass No Grid	0.31	0.27				
	DS Low-E Glass No Grid	0.31	0.27				
	SS Low-E/Argon Glass No Grid	0.28	0.27		MEETS		
	DS Low-E/Argon Glass No Grid	0.28	0.27		MEETS		
	SS Ultra Low-E/Argon No Grid	0.28	0.20		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid	0.28	0.20		MEETS	MEETS	MEETS
	SS Clear Glass with Grid	0.45	0.51				
	DS Clear Glass with Grid	0.45	0.50				
	SS Low-E Glass with Grid	0.31	0.24				MEETS
	DS Low-E Glass with Grid	0.31	0.24				MEETS
	SS Low-E/Argon Glass with Grid	0.28	0.24		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with Grid	0.28	0.24		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon with Grid	0.28	0.18		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid	0.28	0.18		MEETS	MEETS	MEETS
	SS Clear Glass with SDL	0.45	0.45				
	DS Clear Glass with SDL	0.45	0.44				
	SS Low-E Glass with SDL	0.31	0.24				MEETS
	DS Low-E Glass with SDL	0.31	0.24				MEETS
SS Low-E/Argon Glass with SDL	0.28	0.24		MEETS	MEETS	MEETS	
DS Low-E/Argon Glass with SDL	0.28	0.24		MEETS	MEETS	MEETS	
SS Ultra Low-E/Argon with SDL	0.28	0.16		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon with SDL	0.28	0.16		MEETS	MEETS	MEETS	
8900 Double Hung Triple Pane IG Super Spacer®	SS Low-E/Argon Glass No Grid R-5	0.21	0.23		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass No Grid R-5	0.21	0.23		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon No Grid R-5	0.21	0.18		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon No Grid R-5	0.21	0.18		MEETS	MEETS	MEETS
	SS Low-E/Argon Glass with Grid R-5	0.21	0.23		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with Grid R-5	0.21	0.23		MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon with Grid R-5	0.21	0.18		MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid R-5	0.21	0.18		MEETS	MEETS	MEETS
	SS Low-E/Argon Glass with SDL R-5	0.21	0.21		MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with SDL R-5	0.21	0.21		MEETS	MEETS	MEETS



Atrium Windows Doors

8900 Double Hung Triple Pane IG Super Spacer® with InsulKor™ Foam Option	DS Low-E/Argon Glass with SDL R-5	0.21	0.21	MEETS	MEETS	MEETS	MEETS	
	SS Ultra Low-E/Argon with SDL R-5	0.21	0.14	MEETS	MEETS	MEETS	MEETS	
	DS Ultra Low-E/Argon with SDL R-5	0.21	0.14	MEETS	MEETS	MEETS	MEETS	
	SS Low-E/Argon Glass No Grid R-5	0.20	0.23	MEETS	MEETS	MEETS	MEETS	
	DS Low-E/Argon Glass No Grid R-5	0.20	0.23	MEETS	MEETS	MEETS	MEETS	
	SS Ultra Low-E/Argon No Grid R-5	0.20	0.18	MEETS	MEETS	MEETS	MEETS	
	DS Ultra Low-E/Argon No Grid R-5	0.20	0.18	MEETS	MEETS	MEETS	MEETS	
	SS Low-E/Argon Glass with Grid R-5	0.20	0.21	MEETS	MEETS	MEETS	MEETS	
	DS Low-E/Argon Glass with Grid R-5	0.20	0.21	MEETS	MEETS	MEETS	MEETS	
	SS Ultra Low-E/Argon with Grid R-5	0.20	0.16	MEETS	MEETS	MEETS	MEETS	
	DS Ultra Low-E/Argon with Grid R-5	0.20	0.16	MEETS	MEETS	MEETS	MEETS	
	SS Low-E/Argon Glass with SDL R-5	0.20	0.21	MEETS	MEETS	MEETS	MEETS	
	DS Low-E/Argon Glass with SDL R-5	0.20	0.21	MEETS	MEETS	MEETS	MEETS	
	SS Ultra Low-E/Argon with SDL R-5	0.20	0.14	MEETS	MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon with SDL R-5	0.20	0.14	MEETS	MEETS	MEETS	MEETS		
8900 Horizontal Sliders Dual Pane IG	SS Clear Glass No Grid	0.45	0.58					
	DS Clear Glass No Grid	0.45	0.57					
	SS Low-E Glass No Grid	0.32	0.28					
	DS Low-E Glass No Grid	0.32	0.28					
	SS Low-E/Argon Glass No Grid	0.29	0.27		MEETS			
	DS Low-E/Argon Glass No Grid	0.29	0.27		MEETS			
	SS Ultra Low-E/Argon No Grid	0.29	0.20		MEETS	MEETS	MEETS	
	DS Ultra Low-E/Argon No Grid	0.29	0.20		MEETS	MEETS	MEETS	
	SS Northern Energy Star No Grid	0.28	0.37	MEETS	MEETS			
	DS Northern Energy Star No Grid	0.28	0.37	MEETS	MEETS			
	SS Clear Glass with Grid	0.45	0.52					
	DS Clear Glass with Grid	0.45	0.51					
	SS Low-E Glass with Grid	0.32	0.25				MEETS	
	DS Low-E Glass with Grid	0.32	0.25				MEETS	
SS Low-E/Argon Glass with Grid	0.29	0.25		MEETS	MEETS	MEETS		
8900 Horizontal Sliders Dual Pane IG	DS Low-E/Argon Glass with Grid	0.29	0.25		MEETS	MEETS	MEETS	
	SS Ultra Low-E/Argon with Grid	0.29	0.18		MEETS	MEETS	MEETS	
	DS Ultra Low-E/Argon with Grid	0.29	0.18		MEETS	MEETS	MEETS	
	SS Northern Energy Star with Grid	0.28	0.34	MEETS	MEETS			
	DS Northern Energy Star with Grid	0.28	0.33	MEETS	MEETS			
	SS Clear Glass with SDL	0.45	0.46					
	DS Clear Glass with SDL	0.45	0.45					
	SS Low-E Glass with SDL	0.32	0.25				MEETS	
	DS Low-E Glass with SDL	0.32	0.25				MEETS	
	SS Low-E/Argon Glass with SDL	0.29	0.25		MEETS	MEETS	MEETS	
	DS Low-E/Argon Glass with SDL	0.29	0.25		MEETS	MEETS	MEETS	
	SS Ultra Low-E/Argon with SDL	0.29	0.16		MEETS	MEETS	MEETS	
	DS Ultra Low-E/Argon with SDL	0.29	0.16		MEETS	MEETS	MEETS	
	8900 Horizontal Sliders Dual Pane IG with InsulKor™ Foam Option	SS Clear Glass No Grid	0.45	0.58				
DS Clear Glass No Grid		0.45	0.57					
SS Low-E Glass No Grid		0.32	0.28					
DS Low-E Glass No Grid		0.32	0.28					
SS Low-E/Argon Glass No Grid		0.28	0.27		MEETS			
DS Low-E/Argon Glass No Grid		0.28	0.27		MEETS			
SS Ultra Low-E/Argon No Grid		0.28	0.20		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon No Grid		0.28	0.20		MEETS	MEETS	MEETS	
SS Clear Glass with Grid		0.45	0.52					
DS Clear Glass with Grid		0.45	0.51					
SS Low-E Glass with Grid		0.32	0.25				MEETS	
DS Low-E Glass with Grid		0.32	0.25				MEETS	
SS Low-E/Argon Glass with Grid		0.28	0.25		MEETS	MEETS	MEETS	
DS Low-E/Argon Glass with Grid		0.28	0.25		MEETS	MEETS	MEETS	
SS Ultra Low-E/Argon with Grid		0.28	0.18		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon with Grid		0.28	0.18		MEETS	MEETS	MEETS	
SS Clear Glass with SDL		0.45	0.46					
DS Clear Glass with SDL		0.45	0.45					
SS Low-E Glass with SDL		0.32	0.25				MEETS	
DS Low-E Glass with SDL		0.32	0.25				MEETS	
SS Low-E/Argon Glass with SDL		0.28	0.25		MEETS	MEETS	MEETS	
DS Low-E/Argon Glass with SDL		0.28	0.25		MEETS	MEETS	MEETS	
SS Ultra Low-E/Argon with SDL		0.28	0.16		MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon with SDL		0.28	0.16		MEETS	MEETS	MEETS	
8900 Horizontal Sliders Triple Pane IG Super Spacer® nXT™		SS Low-E/Argon Glass No Grid R-5	0.21	0.24	MEETS	MEETS	MEETS	MEETS
		DS Low-E/Argon Glass No Grid R-5	0.21	0.23	MEETS	MEETS	MEETS	MEETS
		SS Ultra Low-E/Argon No Grid R-5	0.20	0.18	MEETS	MEETS	MEETS	MEETS
		DS Ultra Low-E/Argon No Grid R-5	0.20	0.18	MEETS	MEETS	MEETS	MEETS
	SS Low-E/Argon Glass with Grid R-5	0.21	0.21	MEETS	MEETS	MEETS	MEETS	
	DS Low-E/Argon Glass with Grid R-5	0.21	0.21	MEETS	MEETS	MEETS	MEETS	
	SS Ultra Low-E/Argon with Grid R-5	0.20	0.16	MEETS	MEETS	MEETS	MEETS	
	DS Ultra Low-E/Argon with Grid R-5	0.20	0.16	MEETS	MEETS	MEETS	MEETS	
	SS Low-E/Argon Glass with SDL R-5	0.21	0.21	MEETS	MEETS	MEETS	MEETS	
	DS Low-E/Argon Glass with SDL R-5	0.21	0.21	MEETS	MEETS	MEETS	MEETS	
	SS Ultra Low-E/Argon with SDL R-5	0.20	0.15	MEETS	MEETS	MEETS	MEETS	
	DS Ultra Low-E/Argon with SDL R-5	0.20	0.15	MEETS	MEETS	MEETS	MEETS	
	8900 Horizontal Sliders Triple Pane IG	SS Low-E/Argon Glass No Grid R-5	0.27	0.27	MEETS	MEETS		
		DS Low-E/Argon Glass No Grid R-5	0.27	0.27	MEETS	MEETS		
SS Ultra Low-E/Argon No Grid R-5		0.27	0.20	MEETS	MEETS	MEETS	MEETS	
DS Ultra Low-E/Argon No Grid R-5		0.27	0.20	MEETS	MEETS	MEETS	MEETS	
SS Low-E/Argon Glass with Grid R-5		0.27	0.25	MEETS	MEETS	MEETS	MEETS	
DS Low-E/Argon Glass with Grid R-5		0.27	0.25	MEETS	MEETS	MEETS	MEETS	



Atrium Windows Doors

Super Spacer® nXt™ with InsulKor™ Foam Option	SS Ultra Low-E/Argon with Grid R-5	0.27	0.18	MEETS	MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid R-5	0.27	0.18	MEETS	MEETS	MEETS	MEETS
	SS Low-E/Argon Glass with SDL R-5	0.27	0.25	MEETS	MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with SDL R-5	0.27	0.25	MEETS	MEETS	MEETS	MEETS
	SS Ultra Low-E/Argon with SDL R-5	0.27	0.16	MEETS	MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with SDL R-5	0.27	0.16	MEETS	MEETS	MEETS	MEETS
8900 Picture Windows Dual Pane	DS Clear Glass No Grid	0.45	0.63				
	DS Low-E Glass No Grid	0.30	0.30		MEETS		
	DS Low-E/Argon Glass No Grid	0.27	0.30	MEETS	MEETS		
	DS Ultra Low-E/Argon No Grid	0.26	0.22	MEETS	MEETS	MEETS	MEETS
	DS Northern Energy Star No Grid	0.27	0.41	MEETS			
	DS Clear Glass with Grid	0.45	0.57				
	DS Low-E Glass with Grid	0.30	0.27		MEETS		
	DS Low-E/Argon Glass with Grid	0.27	0.27	MEETS	MEETS		
	DS Ultra Low-E/Argon with Grid	0.26	0.20	MEETS	MEETS	MEETS	MEETS
	DS Northern Energy Star with Grid	0.27	0.37	MEETS	MEETS		
	DS Clear Glass with SDL	0.45	0.51				
	DS Low-E Glass with SDL	0.30	0.27		MEETS		
	DS Low-E/Argon Glass with SDL	0.27	0.27	MEETS	MEETS		
	DS Ultra Low-E/Argon with SDL	0.26	0.18	MEETS	MEETS	MEETS	MEETS
8900 Picture Windows Dual Pane IG with InsulKor™ Foam Option	DS Clear Glass No Grid	0.45	0.63				
	DS Low-E Glass No Grid	0.30	0.30		MEETS		
	DS Low-E/Argon Glass No Grid	0.26	0.30	MEETS	MEETS		
	DS Ultra Low-E/Argon No Grid	0.26	0.22	MEETS	MEETS	MEETS	MEETS
	DS Clear Glass with Grid	0.45	0.57				
	DS Low-E Glass with Grid	0.30	0.27		MEETS		
	DS Low-E/Argon Glass with Grid	0.26	0.27	MEETS	MEETS		
	DS Ultra Low-E/Argon with Grid	0.26	0.20	MEETS	MEETS	MEETS	MEETS
	DS Clear Glass with SDL	0.45	0.51				
	DS Low-E Glass with SDL	0.30	0.27		MEETS		
	DS Low-E/Argon Glass with SDL	0.26	0.27	MEETS	MEETS		
DS Ultra Low-E/Argon with SDL	0.26	0.18	MEETS	MEETS	MEETS	MEETS	
8900 Picture Windows Triple Pane IG Super Spacer® nXt™	DS Low-E/Argon Glass No Grid R-5	0.18	0.26	MEETS	MEETS		
	DS Ultra Low-E/Argon No Grid R-5	0.18	0.20	MEETS	MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with Grid R-5	0.18	0.23	MEETS	MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid R-5	0.18	0.18	MEETS	MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with SDL R-5	0.18	0.23	MEETS	MEETS	MEETS	MEETS
DS Ultra Low-E/Argon with SDL R-5	0.18	0.16	MEETS	MEETS	MEETS	MEETS	
8900 Picture Windows Triple Pane IG Super Spacer® nXt™ with InsulKor™ Foam Option	DS Low-E/Argon Glass No Grid R-5	0.18	0.26	MEETS	MEETS		
	DS Ultra Low-E/Argon No Grid R-5	0.18	0.20	MEETS	MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with Grid R-5	0.18	0.23	MEETS	MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with Grid R-5	0.18	0.18	MEETS	MEETS	MEETS	MEETS
	DS Low-E/Argon Glass with SDL R-5	0.18	0.23	MEETS	MEETS	MEETS	MEETS
	DS Ultra Low-E/Argon with SDL R-5	0.18	0.16	MEETS	MEETS	MEETS	MEETS